



WOODEN POLES



100 % MADE IN ITALY

CHROMOLIT-CCB TREATMENT (CCO)

Product type: wood protection

Mark of control: diary law nr. 168

Characteristics: it is a water soluble protection medium with a boron, chrome and copper base, active against fungi, harmful insects and termites

Field of action: suitable for all types of building wood both for exteriors and interiors, plumbing systems, palisades, forest farm poles

Processing: especially suitable for impregnating wood in highly technical processes, such as pressure impregnation. For use, see DIN 68800-3

Production of the solution: with the production of 4.5% of the solution, 4.5 Kg of CHROMOLIT CCO are dissolved in 95.5 liters of water = 12 Kg of salt per cubic meter of wood, at a minimum, this process guarantees a duration minimum of 15 years

Wood treatment: the wood to be treated can be dry or semi-dry

Density: 1.25 - 1.4 gr / cm³

Odor: particular

Wood color after impregnation: gray / green

PH value: about 3 (50 g / l of water 20 °)

Active substances: 14.4 - 15% copper oxide, about 5% boron

Fixing auxiliary substances: chrome trioxid

DEBARKED CHESTNUT POLES

DIAMETER / MT	2,00	2,50	2,70	3,00
5 / 7	V	V	V	V
8 / 10	-	-	V	V
11 / 13	-	-	V	V

DEBARKED PINUS POLES

DIAMETER / MT	1,50	1,80	2,00	2,20	2,50	2,75	3,00	3,50	4,00	5,00
3 / 5	V	V	V	V	V	-	-	-	-	-
4 / 6	V	V	V	V	V	V	-	-	-	-
6 / 8	-	V	V	V	V	V	V	-	-	-
8 / 10	-	-	V	V	V	V	V	V	-	-
10 / 12	-	-	V	V	V	V	V	V	V	V
12 / 14	-	-	-	-	-	V	V	V	V	V
14 / 16	-	-	-	-	-	-	-	V	V	V

TURNED POLES

DIAMETER / MT	1,50	1,75	2,00	2,20	2,50	2,75	3,00	3,50	4,00	5,00
5	V	V	V	V	V	-	-	-	-	-
6	V	V	V	V	V	V	-	-	-	-
7	-	V	V	V	V	V	V	-	-	-
8	V	V	V	V	V	V	V	V	V	-
10	-	-	V	V	V	V	V	V	V	-
12	-	-	-	-	V	V	V	V	V	-

Purely informative, the manufacturer reserves the right to modify the technical characteristics of the product at any time.